

X-Seal

Single component, low density, flexible, hydrophobic grout.

Uses

Sealing of water and gasses in mining and civil applications. Reacts with moisture to form a flexible closed cell grout.

Advantages

- **Simple application**
- **Pre-Blended Catalyst**
- **Flexible, absorbs movement**
- **Low expansive pressure**
- **“Self injection” into the finest of fractures**

Packaging

**8 ounce Bottles (20 Per Box)
300 ml Tubes (12 or 6 Per Box)**

Approvals

NSF 61-2007 approved for use with potable water.

Transport

USDOT. Unregulated Class 55

Physical Properties

Density	Free rise	2.25 lbs/ft ³
Low temp. aging	Confirmed	
-20° F (shrinkage)	0% 1 Day	ASTM D-2126
Viscosity	4000 cps	ASTM D-2126
Specific Gravity @ 60° F	1-30%	A-Side
% Solids	100%	
Color	Amber	
Solvents	None	

Test Data

Compressive	25 psi	ASTM D-1621
Shear	171 psi	ASTM C-273
Tensile	30 psi	ASTM D-1623
Elongation	300%	ASTM D-1623

Storage

Store in airtight containers. Product should not be exposed to the atmosphere until application. Product is moisture sensitive. Avoid contact with moisture.

Shelf Life

2 year minimum in unopened containers.

Caution: Always read MSDS prior to use

www.sealguardinc.com