

Dual Component, Highly Reactive, Early Strength, Water Control Grout

Applications

For high flowing water control and I&I applications in manholes, vaults, and other concrete brick or stone structures above or below grade.

<u>Advantages</u>

- Extremely Fast Reaction Time
- Rapid Sealing
- High Early Strength
- Great Migration Into Fractures
- Will Not Wash Out
- Patented Back Flow Prevention



Do not crush containers. Avoid contact with moisture. Store under 80°F 27°C.

Product has a 2 year shelf life in unopened containers.

Packaging

600 ml Tube Sets 5 Gallon pails 55 Gallon Drums

Transport

US D.O.T. Unregulated Class-55

Customer Support

724-625-4550 info@SealGuardInc.com





Uncured Physical Properties

Shrinkage (-20° F)	0% 1 Day	ASTM D-2126
Viscosity (68° F)	200 cps A-side	300 cps B-side
Specific Gravity (60° F)	1.23 A-side	1.04 B-side
Percent Solids	100%	
Color	Amber	
Solvents	None	

Cured Material - Physical Properties

Density – Free Rise	08 PCF	ASTM D-1622
Compressive	900 psi	ASTM D-1621
Tensile	200 psi	ASTM D-638
Shear	190 psi	ASTM D-732

^{**} Thoroughly read all instructions and cautions prior to use **

